

Manufacturer (trade mark):	Clover Germany	Type/Model OEM:	TN3280
Lot/Part number:	TN3280XL	Toner color(s):	Monochrome
Main application:	To be used on the relevant printers according to remanufacturer instructions		
Intended yield:	12000		
	A1J945313 / C3J580870 / C3J580882	Take over value of existing test protocol :	
Test device:		(box)	Yes, from ISO19752
Test climate:			
Temperature:	25	Relative humidity: 48	
Deviations of the determined test conditions			
Tester 1):	Aleksandar Kojic		
Test date:	22.6.2016		

1) If values are taken over from test protocol, the signing person is responsible, that the protocols, from which the values have been taken off, are plausible and correct.

2) Either testing place or place where the protocol is made

Test sample (A)

1	15007
2	14235
3	14112
4	14796
5	14282
6	13960
7	14519
8	14780
9	14223

Used for valuation

Yes

Charge/Serial number

Sample 1
Sample 2
Sample 3
Sample 4
Sample 5
Sample 6
Sample 7
Sample 8
Sample 9

Comparing Sample (B)

1	8000
2	8000
3	8000
4	
5	

Used for valuation

Yes/no
Yes

Charge/Serial number

OEM Sample/Spec
OEM Sample/Spec
OEM Sample/Spec

Administrative checking of health related attributes (5.2)

Is there an EG- Safety Data Sheet of the used toner?

Yes/no **Yes**

If there are no information of the AMES test in the EG Safety Data Sheet

Is there a test report about the AMES test of the used toner?

Yes/no **Not Applicable**

If not: Description All MSDSs mention Ames test

Checking the influence of the toner module on the printer (5.3)

Is the toner leaking less than the original?

Yes/no **Yes**

Is the interaction between printer and toner module acceptable?

Yes/no **Yes**

If not: Description

Checking the initialization (5.4)

Is the print out acceptable right after the toner module has been inserted?

Yes/no **Yes**

If not: Describe fault

Checking the yield number (5.5)

Monochrome

1

2

3

Average (\bar{A} or V)

Yield A: $(A1+A2+A3)/3 = \bar{A}$	15007	14282	13960	14416
Yield V: $(V1+V2+V3)/3 = V$	8000	8000	8000	8000

Alternative:

Yield A: Result of test after ISO/IEC 19752 \bar{A}

Reference to the test protocol:

Test date:

Yield V: Result of test after ISO/IEC 19752 V

Reference to the test protocol:

Test date:

Result: EZ= \bar{A}/V

1,80

Yes

No

Not Applicable

YES

YES

Checking the black print/Color reproduction (5.6.2)

Average value of the 2 areas F test print A1: 25,9

Average value of the 2 areas F comparing print V1: 26

Difference is not higher than $\Delta \leq 5$ for Monochrom

Color difference $\Delta E \leq 18$ for Color Not applicable

Yes/No/Not Applicable

Yes

Yes/No/Not Applicable

Not Applicable

Average value of the 2 areas F test print A2:	25,5			
Average value of the 2 areas F comparing print V2:	26			
Difference is not higher than $\Delta \leq 5$ for Monochrom	0,5	Yes/No/Not Applicable	Yes	
Color difference $\Delta E \leq 18$ for Color	Not applicable	Yes/No/Not Applicable	Not Applicable	
Average value of the 2 areas F test print A3:	26,2			
Average value of the 2 areas F comparing print V3:	25,9			
Difference is not higher than $\Delta \leq 5$ for Monochrom	0,3	Yes/No/Not Applicable	Yes	
Color difference $\Delta E \leq 18$ for Color	Not applicable	Yes/No/Not Applicable	Not Applicable	

Checking the fade (5.6.3)**Monochrome**

Test print A1				
Color values 1 6 A F after 50 pages	1 92,3	6 84,5	A 68,9	F 29,3
Color values 1 6 A F	1	6	A	F
The biggest deviation	0,7	0,7	2,9	6
Comparing print V1				
Color values 1 6 A F after 50 pages	1 93,3	6 83,4	A 66,6	F 26,9
Color values 1 6 A F	1	6	A	F
The biggest deviation	0,2	1,6	1,4	2
Result determination				
Difference $\Delta L \leq 8$	0,5	0,9	1,5	4
Difference within allowed parameters	YES	YES	YES	YES

Test print A2 Monochrome				
Color values 1 6 A F after 50 pages	1 93,6	6 84,6	A 63,8	F 24,4
Color values 1 6 A F	1	6	A	F
The biggest deviation	1,7	2,8	4,5	2,7
Comparing print V2				
Color values 1 6 A F after 50 pages	1 92,8	6 87,3	A 68,4	F 27,6
Color values 1 6 A F	1	6	A	F
The biggest deviation	0,5	1,5	2,9	2,5
Result determination				
Difference $\Delta L \leq 8$	1	1,3	1,6	0,2
Difference within allowed parameters	YES	YES	YES	YES

Test print A3 Monochrome				
Color values 1 6 A F after 50 pages	1 93,2	6 84	A 65,9	F 23,7
Color values 1 6 A F	1	6	A	F
The biggest deviation	0,2	0,6	2,3	3,4
Comparing print V2				
Color values 1 6 A F after 50 pages	1 93,5	6 86,6	A 69,7	F 27,2
Color values 1 6 A F	1	6	A	F
The biggest deviation	0,1	1,6	2,9	2,4
Result determination				
Difference $\Delta L \leq 8$	0,1	1	0,6	1
Difference within allowed parameters	YES	YES	YES	YES

Checking toner adhesion

Test process: visual (tape method):

Is the resistance in between the acceptable parameters?	Yes
If not: Describe deviation	

Checking the grey page/color uniformity (5.6.5)

Are the differences in brightness between the acceptable parameters (pattern B2) $\Delta L \leq 5$?	Yes
If not: Describe deviation	

Checking the background (5.6.6)

Is the background smudge between the acceptable parameters (pattern B1)?	Yes
If not: Describe deviation	

Checking the ghosting (5.6.7)

Is the repeating of the back rectangles in between the acceptable parameters (pattern B2)?

If not: Describe deviation

Yes

Checking toner miscibility (5.6.8)

Is the toner miscibility given?

If not: Describe deviation

N/A

OVERALL RESULT: Passed